



**PRODUITS CHIMIQUES  
SPECIAUX**

## **SCALP MINERALISANT 94**

Strengthening, mineralising agent for stones and mineral coatings.

### **I Applications:**

Penetrating liquid designed to strengthen by mineralising surfaces such as: lime and siliceous stones, brick, concrete, mineral coatings. Atmospheric pollution degrades facades and causes the elimination of their natural binding agents.

### **II Product Advantages:**

- Sophisticated product
- Very easy to work with
- Does not modify water vapour permeability
- Compatible with the water repellents: SCALPFUGE PS 86, SCALPFUGE 35, SCALPFUGE OM 70, SCALP ANTI-TACHE 07
- Does not alter surface qualities
- Can be sprayed

### **III Physicochemical Properties:**

- Solvented colourless liquid
- Density: 0.95 g/cm<sup>3</sup> at 20°C
- PH: Neutral
- Frost resistant
- Flash Point: 36°C

### **IV Instructions for use:**

1. Dilution: SCALP MINERALISANT 94 is ready to the use, do not dilute.
2. Tools: Roller, low-pressure sprayer.
3. Method: Mix SCALP MINERALISANT 94 well. Apply SCALP MINERALISANT 94 from the base upwards until saturation of the surface on a clean and dry surface in two coats at a minimum of 15 minutes interval. Allow the surface to strengthen for about ten days before possible water repellent treatment. For badly degraded surfaces proceed with a new mineralising operation.
4. Application Time: This solution permeates the surface thoroughly.
5. Application Temperature: From 5 to 50 °C. (Efficacy is reduced at extreme temperatures)
6. Application Rate: According to surface porosity.

### **V Precautions for Safe Handling & Use:**

1. Protection of surfaces: Protect surfaces not to be treated.
2. Protection of personnel: Avoid contact with skin and eyes. Do not inhale fumes. Wear gloves. Do not smoke.

### **VI Cleaning of tools:**

Clean tools with white spirit immediately after use.

### **VII Packaging, palletising, storage:**

- 5 kg: carton of 4 X 5 kg
  - 20 kg: pallet of 24 X 20 kg
- Store SCALP MINERALISANT 94 in a cool place away from direct sources of heat.

**Important:** The contents of this documentation result from our experience of the product. We cannot be held responsible for its use in each individual case. It is essential to test areas to be treated beforehand.

SCALP E49a

Created: June 1997/1194

Updated: January 2005



8 - 14, ALLÉE DE BRUXELLES - Z.I. DE LA POUDRETTE - 93320 PAVILLONS SOUS BOIS  
TÉL. : 01 48 48 39 76 - FAX : 01 48 49 80 36 - E - mail : [scalp@scalp-france.fr](mailto:scalp@scalp-france.fr)  
S.A. AU CAPITAL DE 115 500 € - R.C. BOBIGNY B 562 112 227 - C.C.P. PARIS 2727-780 - SITE internet : [www.scalp-france.fr](http://www.scalp-france.fr)